

## PVC-2092

This is a medium molecular weight, film and medical grade, vinyl suspension resin. PVC-2092 is designed for flexible and semi-rigid profile extrusion, calendered and extruded sheet, and blown film applications where consistent particle size distribution, and low contamination, flexible gels and residual VCM levels are important. This resin has excellent clarity, color, plasticizer sorption and thermal stability. Kosher approved.

ASTM Cell Classification	ASTM D1755	GP4-16440
Inherent Viscosity	ASTM D1243	0.92 ± 0.02
Relative Viscosity		2.20
‘K’ Value	DIN 53726	66
Bulk Density, lbs/ft <sup>3</sup> gms/cm <sup>3</sup>	ASTM D1895	32.0 min. 0.512 min.
Percent Volatiles	GGC 02-05-00	0.35 max.
Slurry Contamination, particles/250 gms	GGC 02-22-00	15 max.
Residual Vinyl Chloride monomer, ppm	ASTM D3749	1.0 max.
Hunterlab Color, ‘L’ ‘a’ ‘b’	GGC 02-25-00	96.5 min. 0.05 max. 1.50 max.
Particle Size Distribution percent retained on 40 mesh 60 mesh 200 mesh Pan	ASTM D1921 method A	0 max. 5 max. 16 max. 4 max.

11/03/00 rev. 4

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. These values and sets of properties are based upon laboratory work with small scale equipment and does not necessarily indicate end product performance. Full scale testing and end product use and performance are the responsibility of the Buyer. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

<sup>1</sup> “value” may not be construed as product specifications.